

COLORTEX Sand Textured Paint

Salient features

- ❖ This high build fine textured coating is based on tough and flexible co-polymer emulsion.
- ❖ Light fast pigments and some additives made it resistant to water, U.V., algae, fungus, flaking, chalking, cracking, etc.

TECHNICAL DATA

Areas of Application	:	Masonry, Asbestos, RCC.
Method of Application	:	Brush and Roller.
Consistency	:	Paste like.
Finish	:	Fine textured matt.
Thinner recommended	:	Potable water.
Supply Viscosity on Stormer	:	90±10 krebs at 30°C
Drying at 30°C & 60%r.h	:	
Surface Dry	:	less than 30 minutes
Hard dry	:	minimum 3hrs
Recoating time	:	Minimum 3 hours at 30°C and 60% R.H.
Spreading capacity	:	At thinner ratio 80 :20 by volume of paint to water is 2.5 to 3.5 sq.mtrs./ltrs./2 coats depending on shade and nature of surface.
Minimum dft	:	at above spreading rate 50-55 microns/coats
Shades available	:	As per Shade Card.
Packs Available	:	1 Ltrs., 4 Ltrs., 20 Ltrs.



DIRECTIONS FOR USE :

For desired performance adequate thickness of paint deposition and surface preparation is of utmost importance.

Surface preparation :

Ensure that the surface to be painted is free from any loose paint dust, grease and growth of algae, fungus or moth.

Use of wire brush and water is recommended for this purpose.

Surface imperfections such as cracks, holes etc should be repaired using white cement and fine sand in proper proportion to stop leakage or seepage.

Application :

For repainting job 2 coats with recommended thinning ratio are adequate however for newly plastered surface you can use our Colorsol stabilizing solution as a priming coat or Supremcem Cement Paint. Minimum 4 hrs gap is required between two subsequent coats.

Dilution ratio of paint with portable water can be altered taking in to consideration the nature of surface, climate & dft required, maximum dilution permitted for top coats of paints is 80 : 20 by volume of paint to water.

Horizontal surface should be given one extra coat for better protection.

Do not overthin or overextend the brush.

TECHNICAL AID SERVICE PROVIDED ON REQUEST

Mfd. by : **GODAVARI PAINTS PVT. LTD.**

Tulsiram Gupta Mills Estate, Darukhana, Reay Road, Mumbai 400 010.

Phone : 2372 3227, 2372 1249 Fax : 2377 5814

E-mail : admin@jayantcolor.com Website : www.jayantcolor.com

DEPOTS :

AHMEDABAD, BHIWANDI, NASIK, PUNE, VADODARA

C & F / AGENTS :

KOLHAPUR, COCHIN, DELHI, RAJKOT, VALSAD, BHUJ, KANPUR, JALANDHAR

Information in this leaflet is given in good faith but without warranty. Covering capacity indicated is under ideal conditions in the laboratory on proper prepared surfaces. Consumer is advised to verify the same practically at site as various conditions effects the parameters indicated above.